

HOLLOW YARN MOLD MEMBRANE MODULE

Publication number: JP62144708
Publication date: 1987-06-27
Inventor: AZUMA TATSUO; KUMAMI KAZUHISA
Applicant: DAICEL CHEM
Classification:
- International: B01D63/02; B01D63/00; B01D63/02; B01D63/00;
(IPC1-7): B01D13/01
- European:
Application number: JP19850286734 19851219
Priority number(s): JP19850286734 19851219

Report a data error here

Abstract of JP62144708

PURPOSE: To eliminate cutting troubles caused by breaks of hollow yarn at the interface between the hollow membrane and the adhesive by introducing as protective layers the non-defective adhesive having swelling effect against hollow yarn for the first stage and the defective adhesive without swelling effect for the next stage. **CONSTITUTION:** At the end of a hollow yarn type membrane module, the non-defective layer 3 having partly swelling effect against the hollow yarns 1 such as epoxy adhesive and the like for the first stage and the defective adhesive layer 2 having swelling effect against hollow yarn 1 such as urethane-based adhesive and the like for the next stage are provided. The non-defective adhesive having a high adhesive strength is cured to which each of hollow yarns 1 is adhered and, after arranging the said adhering section to receive most of the working forces during operation, part of the hollow yarn deteriorated during curing process with the non-defective adhesive is allowed to come into the protective coating layer by introducing the defective adhesive as protective coating layer and cured. Through the said process, provided a force of lateral direction acts on the hollow yarn, the protective layer is not transformed to prevent the hollow yarn from being sharply curved.

Data supplied from the esp@cenet database - Worldwide